

CLAIMS

1. Article comprising at least fibres and/or fibrils, characterized in that the fibres and
5 fibrils are formed from a polymer blend comprising at least:
- a thermally stable polymer; and
 - a thermoplastic polymer chosen from the group of polysulphides and polysulphones.
- 10 2. Article according to Claim 1, characterized in that the thermally stable polymer is chosen from aromatic polyamides, aromatic polyamide-imides, or polyimides.
- 15 3. Article according to Claim 1 or 2, characterized in that the thermoplastic polymer is chosen from polyether sulphone or polyphenylene sulphone.
- 20 4. Article according to one of the preceding claims, characterized in that the thermoplastic polymer and the thermally stable polymer are soluble in the same solvent.
- 25 5. Article according to one of the preceding claims, characterized in that the polymer blend comprises at least 10% by weight of thermoplastic polymer.
6. Article according to one of the preceding claims, characterized in that the fibres are

obtained by blending the thermally stable polymer with the thermoplastic polymer, and then spinning the blend.

7. Article according to Claim 6,
characterized in that the blend is produced by
5 dissolving the polymers in a solvent.

8. Article according to Claim 7,
characterized in that the solvent is an aprotic polar
solvent.

9. Article according to Claim 8,
10 characterized in that the solvent is chosen from DMEU,
DMAC, NMP and DMF.

10. Article according to one of Claims 6 to
8, characterized in that the spinning is wet spinning.

11. Article according to one of Claims 6 to
15 8, characterized in that the spinning is dry spinning.

12. Article according to one of the
preceding claims, characterized in that the fibrids are
obtained by blending the thermally stable polymer with
the thermoplastic polymer, and then precipitating the
20 blend under a shear stress.

13. Article according to one of the
preceding claims, characterized in that it is a
non-woven article.

14. Article according to one of the
25 preceding claims, characterized in that it is obtained
by "web-forming" at least the fibres and/or fibrids by
a "drylaid" process and "consolidation" of the

structure obtained.

15. Article according to one of Claims 1 to 13, characterized in that it is obtained by "web-forming" at least the fibres and/or fibrids by a "wetlaid" process and "consolidation" of the structure obtained.

16. Article according to one of the preceding claims, characterized in that the "consolidation" is carried out by thermal pressing at a temperature greater than the glass transition temperature of the thermoplastic polymer of the fibres and/or fibrids of the invention contained in the article.

17. Fibre, characterized in that it is formed from a polymer blend comprising at least:

- a thermally stable polymer; and
- a thermoplastic polymer chosen from the group of polysulphides and polysulphones;

and in that it has a linear density of less than or equal to 13.2 dtex.

18. Fibrid, characterized in that it is formed from a polymer blend comprising at least:

- a thermally stable polymer; and
- a thermoplastic polymer chosen from the group of polysulphides and polysulphones.

19. Use of the article according to one of Claims 1 to 16 in the electrical insulation field.

Articles comprising fibres and/or fibrids, fibres and
fibrids and process for obtaining them

5

The present invention relates to novel
articles, especially non-woven articles comprising
fibres and/or fibrids. It also relates to novel fibres
and fibrids and to a process for obtaining these fibres
10 and fibrids.